



FOSTERING RELIABILITY

PRODUCT DATA SHEET

Sirigiriplast®-520

Advanced Concrete Plasticizer

DESCRIPTION

Sirigiriplast®-520 is the latest development of super plasticizer for concrete. It meets the requirements for high range water reducing super plasticizers.

USES

Sirigiriplast®-520 is a unique multipurpose super plasticizer that is particularly suitable for the production of ready mixed concrete. Additionally it provides high water reduction and improved fresh concrete characteristics. With its outstanding cost / performance Sirigiriplast®-520 is used for the following:

- Concrete with high water reduction
- High efficient concrete applications
- A wide range of applications where excellent workability is requested
- Variable use in different concrete systems with different raw materials

CHARACTERISTICS / ADVANTAGES

Sirigiriplast®-520 is a powerful superplasticiser based on advanced technology which gives the following advantages:

- High efficiency even at low dosage rates
- Strong water reduction, resulting in high density, high strength and reduced permeability
- Less sensitive against variations in aggregates and / or different cement types
- Extended workability in conjunction with subsequent strength development
- Superior plasticizing effect, resulting in improved flow, placing and compaction characteristics

APPROVALS / STANDARDS

IS 9103, ASTM C494

PRODUCT INFORMATION

Chemical Base	Modified Polycarboxylate
Packaging	255 kg HDPE carboy or Tanker supply
Appearance / Colour	Light Brown Liquid
Shelf Life	12 months from date of production if stored properly in undamaged un opened, original sealed packaging.
Storage Conditions	Store in dry conditions at temperatures between +10°C and +40°C. Protect from direct sunlight and frost.
Density	~1.09 kg/l at 25°C
pH	≥ 6

APPLICATION INFORMATION

Recommended Dosage	0.2 % to 2.0 b. w. o. c. Optimum dosage has to be finalized through site trial. Stir well before use.
Compatibility	Sirigiriplast®-520 may be combined with many other Sirigiri® products. Compatible with all types of cements and cementitious materials. Important: Always conduct trials before combining products in specific mixes and combinations.

APPLICATION INSTRUCTIONS

DISPENSING

Sirigiriplast®-520 can be added into the mixing water or directly into the concrete mixer after 50 – 70% of the mixing water has been added.

The addition of Sirigiriplast®-520 to dry aggregate or cement is not recommended.

To achieve optimum performance a minimum wet mixing time, which is depending on the mixing conditions and the mixer performance, of 60 seconds is recommended.

LIMITATIONS

Excessive water addition or overdosing may cause bleeding or segregation. Overdosing may cause extension of initial and final setting time. If frozen and / or if precipitation has occurred, Sirigiriplast®-520 may be used after thawing slowly at room temperature and after intensive mixing.

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

Sirigiri Corporate Pvt. Ltd.
Survey no # 221, KIADB
Gamanagatti, plot no 101,
Industrial area
Hubballi, Karnataka 580025
India
Tel : +91 9480598115
Fax: +91 836 3551162
Mail : sirigiricorporate@gmail.com



Product Data Sheet
Sirigiriplast®-520
January 2025, Version 06
20250106000000001406

LOCAL RESTRICTIONS

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Material Safety Data Sheet containing physical, ecological, toxicological and other safety related data

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sirigiri products, are given in good faith based on Sirigiri's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sirigiri's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sirigiri reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.



FOSTERING RELIABILITY